



An overview of Mechanical properties of Nano-composites

Mohammed Ridha H .Alhakeem

Ministry of Oil, Midland Refineries company, Baghdad, Iraq

<https://orcid.org/0000-0002-2429-5742>

mu_1978@yahoo.com



*Corresponding Author

Article History:

Submitted: 06-09-2022

Accepted: 08-07-2022

Published: 09-08-2022

Keywords:

Nano composites, micro-machinability, an isotropic, heterogeneous

International journal of
Multidisciplinary Sciences and
Arts is licensed under a Creative
Commons Attribution-
NonCommercial 4.0 International
(CC BY-NC 4.0).

ABSTRACT

Due to the anisotropic, heterogeneous structure, and advanced mechanical properties of these materials combined with the size effects in micromachining, micromachining of nanocomposites is thought to be a challenging operation. In terms of high cutting force, poor surface quality, and rapid tool wear, it results in worse machinability. The first of these two parts of this review paper will provide a thorough overview of the mechanical characteristics of diverse nanocomposites, while the second part will concentrate on the micro-machinability of these nanocomposite materials.

INTRODUCTION

Blumstein used the term "Nano composite" for the first time in 1961 [1]. In an effort to increase the heat stability of nano-silicate reinforced polymethyl methacrylate (PMMA), the primitive nanocomposite was researched [2] in 1965. In terms of their constituents, Nano composites are comparable to traditional composites, with the exception of the size of the reinforcement, which is typically in the range of hundreds of nanometers. While requiring significantly less filler than conventional composites (hereinafter referred to as composites or conventional composites for short), the drop from micro-range to Nano-range of fillers offers amazing reinforcing in nanocomposites, resulting in negligible weight increases [3]. Due to their superior properties, including mechanical [7], thermal [8], electrical [9], electrochemical [10], electromagnetic [10], and gas barrier properties [11], many nanocomposites have been discovered and commercially used in a variety of industrial fields, including (but not limited to) aerospace [4], automobile [5], and medicine [6]. Due to these excellent qualities, Nano composites have found additional uses in the creation of microstructured components, continuing the modern manufacturing trend of downsizing. The Microelectronics has benefited greatly from the use of Nano composites [12]. Due to its perfect electrical conductivity, storage modulus, and environmental stability, carbon nanotubes (CNTs) reinforced polyimide nanocomposite is suitable for microelectronics devices, according to Tang et al. [13]. In contrast to their clean matrix equivalents, some applications, such as high performance transistors made of poly-4-vinylphenol (PVP)/TiO₂ nanocomposite [14] or high energy density capacitors made of poly-vinylidene fluoride/TiO₂ nanocomposite [15], have demonstrated superior performance. Furthermore, this trend toward shrinking might apply to both micromechanical and microelectronic components. When creating micro-products, nanocomposites may be used as an alternative to composites and alloys [16]. For instance, CNTs or carbon nanofiber (CNF) nanocomposites with greater strength-to-weight ratio and flexibility could replace conventional composites [19] such as carbon fibre, glass fibre, or Kevlar reinforced plastics in the manufacture of airframe [17] or wings [18] of micro-air vehicles (MAVs). CNT/Epoxy and CNT/PP nanocomposites have been used by Kumar et al. to create the artificial wings for MAVs [20]. The tri biological property, wear-resistance, and general mechanical properties of metal nanocomposites were further enhanced by the addition of ceramic nanoparticles [21]. As a result, these Nano composites could be employed to create micro-gears [23], linkage rods, or pistons [22]. It would be required to research the mechanical properties as well as workable processing methods to create Nano composites due to their enormous potential to develop micro-products. In terms of dimensional and geometrical accuracy as well as surface quality, the majority of current methods for creating Nano composites (Tcan only produce a near-net-shape. Post-processing or finishing technologies will therefore always be necessary. Several production techniques, including LIGA (Lithography, Electroplating, and Micro extrusion additive manufacturing [26], laser micromachining [25], and molding) [24], Mechanical micromachining and micro-EDM (Electrical Discharge Machining) [27] In order to create tiny, precise components and micro-structured components [29].



NANO COMPOSITES

While their final properties depend on the bonding at the matrix-filler interface, the arrangement of fillers inside the matrix, as well as the geometry and content of the fillers, nanocomposites typically retain the unique characteristics of both the matrix and the fillers that distinguish them from alloys. Nanocomposites also differ from composites in which one of the filler's diameters is between one and one hundred nanometers (nm). The next sections will go through each category's distinct characteristics as well as how filler phases affect them. The potential or commercial applications of various nanocomposites will be discussed in light of their distinctive features. Parallel to the explanation of nanocomposites, a comparison between nanocomposites and composites will be made in order to highlight the key distinctions between them in terms of the effects of filler content, size, and characteristics.

COMPARISON OF COMPOSITES AND NANO COMPOSITES

As was already established, the size of the fillers is the primary distinction between nanocomposites and conventional composites. The size of the fillers has shrunk from a few millimetres in classic composites to micro-scale (1-100 μm) in modern composites, and more recently, nanocomposites with fillers with dimensions in the nanometer range. The primary goal of filler size reduction is to achieve homogeneous filler distribution within the matrix, which will lower stress concentrations inside the composite structure and ultimately improve its mechanical properties [30]. Additionally, smaller fillers have greater surface energies, which create stronger bonds with the matrix [31] and increase the system's stiffness and strength [32]. Essentially, based on the filler scale, there are two primary types of composite reinforcing mechanisms. The continuous mechanism is used to explain micro-fillers, showing that they bear a portion of the load supplied from the matrix and that the stickiness of the matrix-filler contact determines how effective reinforcement is [33]. The strengthening method is used for nano-filler (10–100 nm) when the interaction between the matrix and filler occurs at the molecular level. According to this method, the nano-fillers prevent the matrix from deforming plastically by preventing its dislocations, which increases the material's strength and hardness.

The impact of filler size on the mechanical characteristics of polymer composites has been studied by certain researchers. It was found that the size of fillers had no discernible impact on the tensile modulus of composites in the micro-range. Several experimental findings suggested that employing different particle sizes of Al_2O_3 (1-12 μm), glass (4.5-62 μm), or silica (2-47 μm) did not significantly improve or even worsen the moduli of epoxy-based composites [34]. With PP/ CaCO_3 [38], poly-benzoxazine/ CaCO_3 [39], or polyester/Al [40], the similar tendency was discernible. Additionally, it's unclear how filler size and composite tensile strength relate to one another. While some research claimed that utilising micro silica particles to strengthen epoxy, tensile strengths of composites significantly increased with the reduction in filler size [37, 41], another result showed no trend of tensile strength variation of epoxy/ Al_2O_3 when decreasing the filler size [35]. In general, it can be seen that the effect of filler size on the mechanical properties of composites at the microscale is negligible. The discussion above demonstrates the need to explore the impact of filler size at nanoscales in order to determine whether or not their impact on the mechanical characteristics of composites is more sensitive than that of their micro-counterparts. Snail shell powder in different filler sizes (150, 300, and 420 nm) was modified by Onuegbu and Igwe [42] to reinforce PP. With the reduction of filler size, it was seen that the tensile modulus, flexural strength, and impact strength all improved. These improvements weren't significant, though. For each weight fraction, for instance, the tensile strengths rose by about 5% when the filler size was reduced from 300 to 150 nm. Only when the filler size was kept below 100 nm did the mechanical characteristics of composites significantly improve. This effect was confirmed when Devaprakasam et al. [43] conducted a comparison of micro and nano-fillers in terms of the mechanical performance of polymer composites. This study used nano- and micro-silica with sizes ranging from 40 to 60 nm, and the results showed that the nanocomposite had less change in its modulus and hardness than the composite when varied loadings were applied. The uniform distribution of nano-fillers and their stronger interfacial matrix-filler bonding in comparison to micro-fillers were used to explain the phenomenon, some more studies also revealed that filler sizes had a dominant impact on mechanical properties when they were lowered below 20 nm. A considerable degree of reinforcement could be achieved utilizing fillers with diameters in < 100 nm, which was also confirmed by Edwards [44]. According to [45], "critical size" refers to the filler size threshold at which the mechanical characteristics of composites noticeably improve. The influence of CNTs ratio on the strengthening behaviour of polyethylene-based nanocomposites was studied by Kumar et al. [46].

They stated that the high contact surface area and robust interfacial bonding of CNT-polymer allowed for a significant improvement in hardness and elastic modulus when using high-aspect-ratio CNTs. Additionally, because of the smaller diameter and longer length of high-aspect-ratio CNT, mechanical locking was more common. Although some theoretical models or simulations were discovered, the majority of the pertinent studies exclusively focused on experimental work. To give quantitative analysis and explanation of the strengthening mechanism, constitutive models would be necessary. In order to examine the impact of matrix density, chemical cross-links at the interface, and morphological CNT defects on interfacial shear strength (ISS) and, subsequently, CNT pull-out, Chowdhury and Okabe [47] utilised the molecular dynamic (MD) approach. From the simulation, it was established that high matrix density, presence of cross-link and small cross-link switching contributed to high ISS. Additionally, the effects of CNT waviness, diameter, volume fraction, Poisson's ratio, and matrix modulus on the interfacial strength of polymer/SWCNT have been evaluated using a 3D



representative volume element (RVE) technique [48]. Based on the aforementioned investigations, it can be concluded that determining the interfacial bonding between Nano fiber and matrix is crucial for determining load transmission and, consequently, the effectiveness of the reinforcement's mechanical strengthening. Xiao and Zhang [49] examined the stress transmission behavior of SWCNT in an epoxy matrix using the Cox model for solid fibers [50].

Stress transfer efficiency, which is the ratio of the maximum tensile stress (max) to the maximum shear stress (max) in the interfacial section, served as the primary indicator. Illustrates the impact of SWCNT length, diameter, and thickness. Additionally, a comparison of the effectiveness of stress transfer between carbon fiber (CF) and SWCNT has also been made, assuming that CF has the same hollow structure and dimensions as SWCNT. The analytical findings demonstrated a notable (128%) improvement in epoxy/SWCNT composite over epoxy/CF composite. This improvement was caused by an increase in Young's modulus and a structural change (from a solid to a hollow construction), which contributed 69% and 31%, respectively. This led to the conclusion that, when compared to their micro-counterpart, Nano-fibers with higher aspect ratio and tensile characteristics can offer higher reinforcing efficiency. According to some researchers, utilizing Nano-fillers at lower loadings than micro-fillers can yield an identical or even greater strengthening effect. According to Fornes [51], whereas the same result might be obtained by employing three times the amount of glass fibre or more nano-clay montmorillonite (MMT) platelets, the modulus of nylon 6 would be doubled by mixing only around 6.5 wt.% of these platelets. According to Campbell [52], a composite may attain the requisite strength and stiffness when utilising either 70 wt% or 50 wt% of micro-fibers. Since Nano composites have proven to be an effective material to use in demanding applications that require excellent strength to weight ratio, it can be seen that they can provide excellent mechanical properties with low filler contents, which can only be obtained using high filler content in conventional composites [53]. Li and Saigal [54] used shear-lag analysis and the representative volume element (RVE) to confirm the improvement in stress transfer efficiency caused by the increase in nanotube diameter. They also took into account the influence of fibre volume percent, which was not taken into account in other investigations. Researchers also looked at the mechanisms underlying the strengthening effectiveness of nano-fillers such CNT in MMNCs, which include load transfer [50], Orowan strengthening [55], and thermal expansion mismatch [56]. According to [58], the addition of CNT led to an increase in strength that was caused by the metal matrix's refined particle size [57]. The effect of reinforcement size also considerably influenced the strengthening behaviour of MMNCs, similar to polymer-based nanocomposites [59–61]. However, only a few published models offered a thorough justification for the CNT reinforced MMNCs' strengthening mechanism. To evaluate the elastoplastic behaviour of CNT reinforced MMNCs, Barai and Weng [62] created a two-scale model, taking into account the interface characteristics and CNT aggregation as the two key elements impacting the load transfer. The effect of both the matrix grain size and the filler size on the strengthening process of metal/CNT nanocomposites was incorporated in a dislocation model created by Dong et al. [63]. They asserted that at small particle size and large CNT volume, the load transfer effect was improved.

MECHANICAL CHARACTERISTICS OF NANO COMPOSITES

It is obvious from the descriptions of the distinctions between nanocomposites and composites in the preceding section that using nano-fillers to reinforce a matrix material could result in greater reinforcement efficacy than due to their cutting-edge mechanical characteristics and unique nanostructures, micro-fillers. CNTs, graphene, and nanoclays are only a few of the latest applications of Nano-fillers. due to their compatibility and great strength, are the most widely used reinforcing materials. Effectiveness of reinforcement using metals, ceramics, and polymers as the three basic matrix materials. The most pertinent studies' primary goal is to examine the differences in terms of density between the clean matrix and the matrix enhanced Nano-fillers the most typical are mechanical, thermal, and electrical qualities. inside the solely the mechanical qualities will be taken into account given the limited needs for the other parts that deal with Nano composites' micromachining. There are numerous variables that can affect how well nano-fillers are reinforced, including divided into three major categories: Nano scale nature, interaction between fillers and matrices, and

(iii) Making up techniques.

NANO COMPOSITES BASED ON CNT

CNTs are carbon allotropes composed of a single layer of carbon atoms that has been rolled up into a cylindrical shape. CNTs have diameters and lengths that range from 0.1 to 100 m and 1-100 nm, respectively [64], and they have a very high aspect ratio due to their tubular structure. Materials having surface areas between 200 and 900 m² per g are available [65]. Iijima made the initial discovery of CNT in a TEM image in 1991 [66], and the same author also created the first single-walled carbon nanotube in 1993 [67]. CNT has been used in a wide variety of industries, including medication delivery [68], healthcare [69], electronics [70], electrics, and thermal applications [71]. CNTs have enormous potential applications on composite reinforcement because of their high strength-to-weight ratio, aspect ratio, thermal, and electrical properties [72, 73].

CNT-REINFORCED NANOCOMPOSITES WITH POLYMER MATRICES

Due to their superior interfacial interaction over ceramic [74] or metal matrix [75] and the analogous characteristics of



organic structure, CNTs have been used to strengthen polymers. In light of this, it has been observed that some polymer/CNT nanocomposites have tensile strengths between 0.1 and 5 GPa and Young's moduli between 5 and 200 GPa [76]. Using CNTs as reinforcement generally improved the mechanical properties of some polymers, including epoxy [77-80], polystyrene (PS) [81], polyethylene [82, 83], PMMA [84, 85], poly (p-phenylene benzobisoxazole) (PBO) [86], polyvinyl alcohol (PVA) [87], polyester elastomers (PEE) [88], polycarbonate (PC) [89], polyamide-6 [90]. To prevent agglomerations or bundles that adversely influence the mechanical properties of PMNCs, typically when CNTs content exceeds 2-3%, the optimal CNT loading must be carefully examined [92]. The detrimental impact on the tensile strength of nanocomposite is specifically caused by the inadequate interfacial interaction between CNT and polyester [93,94, 95, 96, 97]. The most popular dispersion techniques for creating polymer-based nanocomposites are solution mixing, in situ polymerization dry mixing, and melt mixing. The effects of dispersion techniques (dry mixing and solution mixing) on the mechanical characteristics of PP/CNT nanocomposites have been studied by Esawi et al. The outcomes showed that dry-mixing, as opposed to solution-mixing, produced a higher level of CNT distribution. The polymer's breakdown and its high viscosity as a result of the solutions' addition, which restricted the dispersion of CNTs, were factors in the less significant increases in mechanical characteristics when solution-mixing was used. Additionally, using ultrasonication during solution mixing may cause damage to the CNT structure, which has a negative impact on the mechanical strength of nanocomposites [99]. Along with the impact of CNT concentration, extensive evidence points to the influence of CNT structure on the mechanical characteristics of CNT-based nanocomposites. Since CNTs come in a variety of forms, including SWCNTs, double-walled CNTs (DWCNTs), and MWCNTs, their diverse architectures and physical characteristics result in a range of mechanical reinforcing efficacies.. Since SWCNTs and DWCNTs have higher mechanical characteristics, aspect ratios, and specific surface areas than MWCNTs, their inclusion could theoretically result in stronger mechanical properties. Additionally, compared to CNTs with a lower layer structure, MWCNTs have a lower effective surface area due to their multi-layer structure. However, the degree of homogeneity in the CNT distribution within the polymer matrix also affects how successful the reinforcement is. In this instance, DWCNTs did not aggregate like SWCNTs did, which contributed to a greater improvement in tensile characteristics. This phenomena, that MWCNT dispersion inside PC matrix was significantly more effective than SWCNT regardless of the fabrication procedures, was further supported by Fornes et al. [100] and Sennett et al. [101]. In contrast to MWCNT, they claimed that SWCNT had a higher propensity to re-agglomerate during synthesis, making exfoliation more challenging.

The mechanical characteristics of polymer-based nanocomposites are mostly influenced by CNT alignment in addition to structure. Several techniques, including shear flows [102], ex-situ alignment [103], force field and magnetic field-induced alignment [104], electrospinning-induced alignment [106], and liquid crystalline phase-induced alignment [105], could be used to achieve this property.

some experimental findings that demonstrate how aligned CNT-based nanocomposites have improved tensile properties when compared to non-aligned CNT-based nanocomposites. When CNT alignment was used, it may be mostly explained by the isotropic nature of nanocomposites, which also improved distribution and decreased CNT agglomeration when filling into the polymer matrix.

Additionally, functionalization has been regarded as a successful way to strengthen CNTs' interaction adhesions with polymer matrix and, as a result, increase the effectiveness of mechanical characteristics through load transmission. According to Khare et al. [108], adding amido-anime functionalized CNTs (fCNTs) to epoxy reinforcement improved mechanical qualities more than pristine-CNTs (p-CNTs) (by around 51% of Young's modulus). Lower interphase compression, matrix structure integrity, reduction of matrix mobility, stable covalent connections of epoxy-FCNTs, and subsequently facilitated load transmission were some of the primary explanations cited.

The inclusion of CNTs showed various variations of fracture strain and toughness, in contrast to the enhancements of tensile strength and Young's modulus. The fracture strain improvement trends for thermoplastic and thermosetting reinforced by CNTs at varying weight contents. It was shown that each filler loading drastically reduced the flexibility of thermoplastic nanocomposites. Although pertinent investigations have demonstrated this phenomena, a thorough explanation has not yet been put forth. According to Wang et al. [109], a strong interface interaction between the matrix and filler may be to blame for the decrease of flexibility that results from the addition of MWCNT-NH₂ to Polyimide (PI). As a result, the flexibility of this material may be reduced due to restrictions on the mobility of polymer chains under loading. The description of interfacial strength, however, has not been presented to substantiate this assertion. Contrarily, unlike thermoplastic nanocomposites, the fracture stresses of thermosets might be increased by the inclusion of CNTs at specific amounts of content. Chen et al. [110] reported that the scattered CNT toughened the brittle epoxy phase when epoxy was reinforced by MWCNT. Gojny et al. [111] validated this increase in failure strain at certain low filler loadings (below 1 wt%). Higher CNT loadings caused CNT agglomeration, which reduced the fracture strain by concentrating stress and weakening the interfacial contact between the polymer and CNT. These explanations were shown using scanning electron microscope (SEM) images to show the dispersion of CNTs at various filler contents.

Due to their high aspect ratio and stiffness, CNTs have been identified as a viable reinforcing candidate to replace glass fibre (GF) or carbon fibre (CF) in order to increase toughening efficiency [112]. The following is an expression for the micro-mechanical toughening mechanism of polymer reinforced CNT nanocomposites:

The interface strength and applied load have an impact on two CNT properties: (1) fracture bridging by CNTs and (2) CNT de-bonding and pull-out or breaking [113, 114]. On the basis of this schematic, it can be shown that CNTs should



be orientated transversely to the propagated cracks where the bridging mechanism operates in order to attain the highest fracture toughness. If CNTs are distributed randomly or longitudinally, it will not significantly affect fracture toughness [115]. Additionally, the impact of transverse alignment might only work at modest CNT loadings.

According to some research, the fracture toughness of polymer/CNT nanocomposites is enhanced to a maximum of around 51% when 3 weight percent of fillers are utilised, and it decreases when this level is exceeded due to filler agglomeration [115, 116]. However, at low filler contents (1 wt%), the random distribution of CNTs did not exhibit a significant improvement in toughness [117]. Additionally, Chen et al [114] 's analysis of the impact of interface strength and CNT length on fracture toughness. They argued that considering simply the length of the fibres or the interface chemical bond density would not increase fracture toughness; both must be taken into account. These indicators performed best at 5–10% and 100 nm, respectively.

Their experiment has validated this theoretical analysis through optimal CNT-bridging.

The fracture toughness of nanocomposites has also been impacted by the shape of CNTs. Generally, reinforcing polymers with long CNT may achieve high fracture toughness due to its high load transfer and hence boosting the interface shear strength [118, 119].

Due to DWCNT's great compatibility with the epoxy matrix, low concentrations of it (less than 0.5 weight percent) have demonstrated a notable improvement in the fracture toughness of epoxy-based nanocomposites (37). However, MWCNT could be a superior reinforcing candidate to increase fracture toughness than other types of CNTs by adopting proper dispersion techniques and functionalization (18). In general, the link between numerous parameters, including CNT content, structure, alignment, treatment, and processing technique, has revealed a convoluted relationship when it comes to the improvement in fracture toughness when reinforcing polymer with CNTs. With the aforementioned considerations taken into account,

CONCLUSION

This paper's initial section covered pertinent investigations, such as the creation and characterisation of nanocomposites. Based on that, it has been found that the mechanical properties of nanocomposites were improved by the reinforcement provided by nano-fillers. The nature of the filler and matrix, how they interact, the size of the filler, and the fabrication techniques all affect the extent of enhancement. Through modelling and experimental methods, toughening and toughening mechanisms were also used to explain these variances. The review paper's attention has been drawn to nanocomposite materials that must undergo mechanical micromachining procedures to generate the finished article. These include metal/ceramic nanocomposites, polymer/graphene, and polymer/CNT nanocomposites. The mechanical properties will be connected with various machining measures, and this section of the review will serve as the foundation for analysing the machinability of nanocomposites when using mechanical micromachining techniques.

REFERENCES

- [1] A. Blumstein, "ETUDE DES POLYMERISATIONS EN COUCHE ADSORBEE. 1," *Bulletin de la Societe Chimique de France*, pp. 899-&, 1961.
- [2] A. Blumstein, "Polymerization of adsorbed monolayers. II. Thermal degradation of the inserted polymer," *Journal of Polymer Science Part A: General Papers*, vol. 3, pp. 2665-2672, 1965.
- [3] I. Arora, J. Samuel, and N. Koratkar, "Experimental investigation of the machinability of epoxy reinforced with graphene platelets," *Journal of Manufacturing Science and Engineering*, vol. 135, p. 041007, 2013.
- [4] I. Srikantha, P. Ghosalb, A. Kumara, and R. Jaina, "Nanocomposites for Aerospace Applications," *Nanotech*, p. 52.
- [5] J. M. Garces, D. J. Moll, J. Bicerano, R. Fibiger, and D. G. McLeod, "Polymeric nanocomposites for automotive applications," *Advanced Materials*, vol. 12, pp. 1835-1839, 2000.
- [6] D. Feldman, "Polymer nanocomposites in medicine," *Journal of Macromolecular Science, Part A*, vol. 53, pp. 55-62, 2016.
- [7] I. Dinca, C. Ban, A. Stefan, and G. Pelin, "Nanocomposites as advanced materials for aerospace industry," *Incas Bulletin*, vol. 4, p. 73, 2012.
- [8] A. Leszczyńska, J. Njuguna, K. Pielichowski, and J. Banerjee, "Polymer/montmorillonite nanocomposites with improved thermal properties: Part I. Factors influencing thermal stability and mechanisms of thermal stability improvement," *Thermochimica acta*, vol. 453, pp. 75-96, 2007.
- [9] J. Bai and A. Allaoui, "Effect of the length and the aggregate size of MWNTs on the improvement efficiency of the mechanical and electrical properties of nanocomposites—experimental investigation," *Composites Part A: applied science and manufacturing*, vol. 34, pp. 689-694, 2003.
- [10] N. Dong, M. Zhong, P. Fei, Z. Lei, and B. Su, "Magnetic and electrochemical properties of PANiCoFe2O4 nanocomposites synthesized via a novel one-step solvothermal method," *Journal of Alloys and Compounds*, vol. 660, pp. 382-386, 2016.
- [11] Al-Bahrani M, Bouaissi A, Cree A. Mechanical and electrical behaviors of self-sensing nanocomposite-based MWCNTs material when subjected to twist shear load. *Mechanics of Advanced Materials and Structures*. 2021 Jun 23;28(14):1488-97.



- [12] Y. Liu, W. Xiong, L. Jiang, Y. Zhou, and Y. Lu, "Precise 3D printing of micro/nanostructures using highly conductive carbon nanotube-thiol-acrylate composites," in *Laser 3D Manufacturing III*, 2016, p. 973808.
- [13] Q. Y. Tang, Y. C. Chan, N. B. Wong, and R. Cheung, "Surfactant-assisted processing of polyimide/multiwall carbon nanotube nanocomposites for microelectronics applications," *Polymer International*, vol. 59, pp. 1240-1245, 2010.
- [14] F.-C. Chen, C.-W. Chu, J. He, Y. Yang, and J.-L. Lin, "Organic thin-film transistors with nanocomposite dielectric gate insulator," *Applied physics letters*, vol. 85, pp. 3295-3297, 2004.
- [15] H. Tang and H. A. Sodano, "High energy density nanocomposite capacitors using nonferroelectric nanowires," *Applied Physics Letters*, vol. 102, p. 063901, 2013.
- [16] P. M. Raj, H. Sharma, G. P. Reddy, N. Altunyurt, M. Swaminathan, R. Tummla, *et al.*, "Cobalt– polymer nanocomposite dielectrics for miniaturized antennas," *Journal of electronic materials*, vol. 43, pp. 1097-1106, 2014.
- [17] E. Goossen, "Vertical take off and landing unmanned aerial vehicle airframe structure," ed: Google Patents, 2012.
- [18] D. J. Pines and F. Bohorquez, "Challenges facing future micro-air-vehicle development," *Journal of aircraft*, vol. 43, pp. 290-305, 2006.
- [19] R. Vijayanandh, N. Kumar, S. Kumar, R. Kumar, and N. Kumar, "Material Optimization of High Speed Micro Aerial Vehicle using FSI Simulation," *Procedia Computer Science*, vol. 133, pp. 2-9, 2018.
- [20] D. Kumar, T. Goyal, V. Kumar, P. Mohite, S. Kamle, and V. Verma, "Development and modal analysis of bioinspired CNT/epoxy nanocomposite MAV flapping wings," *J. Aerosp. Sci. Technol*, vol. 67, pp. 88-93, 2015.
- [21] X. Sun and J. Li, "Friction and wear properties of electrodeposited nickel–titania nanocomposite coatings," *Tribology Letters*, vol. 28, pp. 223-228, 2007.
- [22] M. Imbaby and K. Jiang, "Fabrication of free standing 316-L stainless steel–Al₂O₃ composite micro machine parts by soft moulding," *Acta Materialia*, vol. 57, pp. 4751-4757, 2009.
- [23] M. Imbaby and K. Jiang, "Stainless steel–titania composite micro gear fabricated by soft moulding and dispersing technique," *Microelectronic Engineering*, vol. 87, pp. 1650-1654, 2010.
- [24] I. Timoshkov, V. Kurmashev, and V. Timoshkov, "Electroplated nanocomposites of high wear resistance for advanced systems application," in *Advances in Nanocomposite Technology*, ed: IntechOpen, 2011.
- [25] R. N. Das, F. D. Egitto, J. M. Lauffer, and V. R. Markovich, "Laser micromachining of nanocomposite-based flexible embedded capacitors," in *2007 Proceedings 57th Electronic Components and Technology Conference*, 2007, pp. 435-441.
- [26] E. N. Udofia and W. Zhou, "A guiding framework for microextrusion additive manufacturing," *Journal of Manufacturing Science and Engineering*, vol. 141, 2019.
- [27] T. Bartkowiak and C. A. Brown, "A Characterization of Process–Surface Texture Interactions in Micro-Electrical Discharge Machining Using Multiscale Curvature Tensor Analysis," *Journal of Manufacturing Science and Engineering*, vol. 140, 2018.
- [28] Al-Bahrani M, Cree A. In situ detection of oil leakage by new self-sensing nanocomposite sensor containing MWCNTs. *Applied Nanoscience*. 2021 Sep;11(9):2433-45.
- [29] E. Brinksmeier, R. Gläbe, O. Riemer, and S. Twardy, "Potentials of precision machining processes for the manufacture of micro forming molds," *Microsystem Technologies*, vol. 14, p. 1983, 2008.
- [30] M. Huang and Z. Li, "Influences of particle size and interface energy on the stress concentration induced by the oblate spheroidal particle and the void nucleation mechanism," *International journal of solids and structures*, vol. 43, pp. 4097-4115, 2006.
- [31] W. Zhou, D. Yu, C. Wang, Q. An, and S. Qi, "Effect of filler size distribution on the mechanical and physical properties of alumina-filled silicone rubber," *Polymer Engineering & Science*, vol. 48, pp. 1381-1388, 2008.
- [32] N. Chisholm, H. Mahfuz, V. K. Rangari, A. Ashfaq, and S. Jeelani, "Fabrication and mechanical characterization of carbon/SiC-epoxy nanocomposites," *Composite structures*, vol. 67, pp. 115124, 2005.
- [33] M. Dekkers and D. Heikens, "The effect of interfacial adhesion on the tensile behavior of polystyrene–glass-bead composites," *Journal of Applied Polymer Science*, vol. 28, pp. 38093815, 1983.
- [34] Q. Zhang, M. Tian, Y. Wu, G. Lin, and L. Zhang, "Effect of particle size on the properties of Mg (OH) 2-filled rubber composites," *Journal of Applied Polymer Science*, vol. 94, pp. 2341-2346, 2004.
- [35] K. Radford, "The mechanical properties of an epoxy resin with a second phase dispersion," *Journal of Materials Science*, vol. 6, pp. 1286-1291, 1971.
- [36] J. Spanoudakis and R. Young, "Crack propagation in a glass particle-filled epoxy resin," *Journal of Materials Science*, vol. 19, pp. 473-486, 1984.



- [37] Y. Nakamura, M. Yamaguchi, M. Okubo, and T. Matsumoto, "Effect of particle size on mechanical properties of epoxy resin filled with angular-shaped silica," *Journal of applied polymer science*, vol. 44, pp. 151-158, 1992.
- [38] A. Lazzeri, Y. Thio, and R. Cohen, "Volume strain measurements on CaCO₃/polypropylene particulate composites: the effect of particle size," *Journal of applied polymer science*, vol. 91, pp. 925-935, 2004.
- [39] N. Suprapakorn, S. Dhamrongvaraporn, and H. Ishida, "Effect of CaCO₃ on the mechanical and rheological properties of a ring-opening phenolic resin: Polybenzoxazine," *Polymer composites*, vol. 19, pp. 126-132, 1998.
- [40] Al-Abboodi H, Fan H, Mhmood IA, Al-Bahrani M. The dry sliding wear rate of a Fe-based amorphous coating prepared on mild steel by HVOF thermal spraying. *Journal of Materials Research and Technology*. 2022 May 1;18:1682-91.
- [41] A. Roulin-Moloney, W. Cantwell, and H. Kausch, "Parameters determining the strength and toughness of particulate-filled epoxy resins," *Polymer composites*, vol. 8, pp. 314-323, 1987.
- [42] G. C. Onuegbu and I. O. Igwe, "The effects of filler contents and particle sizes on the mechanical and end-use properties of snail shell powder filled polypropylene," *Materials Sciences and Applications*, vol. 2, p. 810, 2011.
- [43] Al-Bahrani M. *The Manufacture and Testing of Self-Sensing CNTs Nanocomposites for Damage Detecting Applications* (Doctoral dissertation, University of Plymouth).
- [44] D. Edwards, "Polymer-filler interactions in rubber reinforcement," *Journal of Materials Science*, vol. 25, pp. 4175-4185, 1990.
- [45] O. Kamigaito, "What can be improved by nanometer composites?," *Journal of the Japan Society of Powder and Powder Metallurgy*, vol. 38, pp. 315-321, 1991.
- [46] R. M. Kumar, S. K. Sharma, B. M. Kumar, and D. Lahiri, "Effects of carbon nanotube aspect ratio on strengthening and tribological behavior of ultra high molecular weight polyethylene composite," *Composites Part A: Applied Science and Manufacturing*, vol. 76, pp. 62-72, 2015.
- [47] S. Chowdhury and T. Okabe, "Computer simulation of carbon nanotube pull-out from polymer by the molecular dynamics method," *Composites Part A: Applied Science and Manufacturing*, vol. 38, pp. 747-754, 2007.
- [48] K. Yazdchi and M. Salehi, "The effects of CNT waviness on interfacial stress transfer characteristics of CNT/polymer composites," *Composites Part A: Applied Science and Manufacturing*, vol. 42, pp. 1301-1309, 2011.
- [49] K. Xiao and L. Zhang, "The stress transfer efficiency of a single-walled carbon nanotube in epoxy matrix," *Journal of Materials Science*, vol. 39, pp. 4481-4486, 2004.
- [50] H. Cox, "The elasticity and strength of paper and other fibrous materials," *British journal of applied physics*, vol. 3, p. 72, 1952.
- [51] T. Fornes and D. Paul, "Modeling properties of nylon 6/clay nanocomposites using composite theories," *polymer*, vol. 44, pp. 4993-5013, 2003.
- [52] F. C. Campbell, *Structural composite materials*: ASM international, 2010.
- [53] A. Bhattacharya, K. Ganguly, A. De, and S. Sarkar, "A new conducting nanocomposite—PPy/zirconium (IV) oxide," *Materials research bulletin*, vol. 31, pp. 527-530, 1996.
- [54] K. Li and S. Saigal, "Micromechanical modeling of stress transfer in carbon nanotube reinforced polymer composites," *Materials Science and Engineering: A*, vol. 457, pp. 44-57, 2007.
- [55] S. Yoo, S. Han, and W. Kim, "Strength and strain hardening of aluminum matrix composites with randomly dispersed nanometer-length fragmented carbon nanotubes," *Scripta Materialia*, vol. 68, pp. 711-714, 2013.
- [56] H. Choi, B. Min, J. Shin, and D. Bae, "Strengthening in nanostructured 2024 aluminum alloy and its composites containing carbon nanotubes," *Composites Part A: Applied Science and Manufacturing*, vol. 42, pp. 1438-1444, 2011.
- [57] K. M. Youssef, R. O. Scattergood, K. L. Murty, J. A. Horton, and C. C. Koch, "Ultrahigh strength and high ductility of bulk nanocrystalline copper," *Applied Physics Letters*, vol. 87, p. 091904, 2005.
- [58] D. H. Nam, S. I. Cha, B. K. Lim, H. M. Park, D. S. Han, and S. H. Hong, "Synergistic strengthening by load transfer mechanism and grain refinement of CNT/Al-Cu composites," *Carbon*, vol. 50, pp. 2417-2423, 2012.
- [59] M. Ashby, "The deformation of plastically non-homogeneous materials," *The Philosophical Magazine: A Journal of Theoretical Experimental and Applied Physics*, vol. 21, pp. 399-424, 1970.
- [60] C.-W. Nan and D. Clarke, "The influence of particle size and particle fracture on the elastic/plastic deformation of metal matrix composites," *Acta materialia*, vol. 44, pp. 3801-3811, 1996.
- [61] D. Lloyd, "Particle reinforced aluminium and magnesium matrix composites," *International materials reviews*, vol. 39, pp. 1-23, 1994.



- [62] Al-Bahrani M, Majdi HS, Abed AM, Cree A. An innovated method to monitor the health condition of the thermoelectric cooling system using nanocomposite-based CNTs. *International Journal of Energy Research*. 2022 May;46(6):7519-28.
- [63] S. Dong, J. Zhou, D. Hui, Y. Wang, and S. Zhang, "Size dependent strengthening mechanisms in carbon nanotube reinforced metal matrix composites," *Composites Part A: Applied Science and Manufacturing*, vol. 68, pp. 356-364, 2015.
- [64] B. Han, S. Sun, S. Ding, L. Zhang, X. Yu, and J. Ou, "Review of nanocarbon-engineered multifunctional cementitious composites," *Composites Part A: Applied Science and Manufacturing*, vol. 70, pp. 69-81, 2015.
- [65] X.-L. Xie, Y.-W. Mai, and X.-P. Zhou, "Dispersion and alignment of carbon nanotubes in polymer matrix: a review," *Materials science and engineering: R: Reports*, vol. 49, pp. 89-112, 2005.
- [66] S. Iijima, "Helical microtubules of graphitic carbon," *nature*, vol. 354, p. 56, 1991.
- [67] S. Iijima and T. Ichihashi, "Single-shell carbon nanotubes of 1-nm diameter," *nature*, vol. 363, p. 603, 1993.
- [68] B. Singh, C. Baburao, V. Pispati, H. Pathipati, N. Muthy, S. Prassana, *et al.*, "Carbon nanotubes. A novel drug delivery system," *International Journal of Research in Pharmacy and Chemistry*, vol. 2, pp. 523-532, 2012.
- [69] S. Kumar, R. Rani, N. Dilbaghi, K. Tankeshwar, and K.-H. Kim, "Carbon nanotubes: a novel material for multifaceted applications in human healthcare," *Chemical society reviews*, vol. 46, pp. 158-196, 2017.
- [70] L.-M. Peng, Z. Zhang, and S. Wang, "Carbon nanotube electronics: recent advances," *Materials today*, vol. 17, pp. 433-442, 2014.
- [71] M. F. De Volder, S. H. Tawfick, R. H. Baughman, and A. J. Hart, "Carbon nanotubes: present and future commercial applications," *science*, vol. 339, pp. 535-539, 2013.
- [72] H. Cebeci, R. G. de Villoria, A. J. Hart, and B. L. Wardle, "Multifunctional properties of high volume fraction aligned carbon nanotube polymer composites with controlled morphology," *Composites Science and Technology*, vol. 69, pp. 2649-2656, 2009.
- [73] A. Allaoui, S. Bai, H.-M. Cheng, and J. Bai, "Mechanical and electrical properties of a MWNT/epoxy composite," *Composites science and technology*, vol. 62, pp. 1993-1998, 2002.
- [74] S. S. Samal and S. Bal, "Carbon nanotube reinforced ceramic matrix composites-a review," 2008.
- [75] N. Silvestre, "State-of-the-art review on carbon nanotube reinforced metal matrix composites," *International Journal of Composite Materials*, vol. 3, pp. 28-44, 2013.
- [76] W. Lu, M. Zu, J. H. Byun, B. S. Kim, and T. W. Chou, "State of the art of carbon nanotube fibers: opportunities and challenges," *Advanced materials*, vol. 24, pp. 1805-1833, 2012.
- [77] X. Gong, J. Liu, S. Baskaran, R. D. Voise, and J. S. Young, "Surfactant-assisted processing of carbon nanotube/polymer composites," *Chemistry of materials*, vol. 12, pp. 1049-1052, 2000.
- [78] Y. Breton, S. Delpeux, R. Benoit, J. Salvétat, C. Sinturel, F. Beguin, *et al.*, "Functionalization of multiwall carbon nanotubes: properties of nanotubes-epoxy composites," *Molecular Crystals and Liquid Crystals*, vol. 387, pp. 135-140, 2002.
- [79] J. Zhu, H. Peng, F. Rodriguez-Macias, J. L. Margrave, V. N. Khabashesku, A. M. Imam, *et al.*, "Reinforcing epoxy polymer composites through covalent integration of functionalized nanotubes," *Advanced Functional Materials*, vol. 14, pp. 643-648, 2004.
- [80] J. Zhu, J. Kim, H. Peng, J. L. Margrave, V. N. Khabashesku, and E. V. Barrera, "Improving the dispersion and integration of single-walled carbon nanotubes in epoxy composites through functionalization," *Nano letters*, vol. 3, pp. 1107-1113, 2003.
- [81] R. Haggemueller, W. Zhou, J. Fischer, and K. Winey, "Production and characterization of polymer nanocomposites with highly aligned single-walled carbon nanotubes," *Journal of nanoscience and nanotechnology*, vol. 3, pp. 105-110, 2003.
- [82] W. Tang, M. H. Santare, and S. G. Advani, "Melt processing and mechanical property characterization of multi-walled carbon nanotube/high density polyethylene (MWNT/HDPE) composite films," *Carbon*, vol. 41, pp. 2779-2785, 2003.
- [83] Y. Bin, M. Kitanaka, and D. Zhu, "Flow-induced properties of nanotube-filled polymer materials," *Macromolecules*, vol. 36, pp. 213-6, 2003.
- [84] J. Zeng, B. Saltysiak, W. Johnson, D. A. Schiraldi, and S. Kumar, "Processing and properties of poly (methyl methacrylate)/carbon nano fiber composites," *Composites Part B: Engineering*, vol. 35, pp. 173-178, 2004.
- [85] C. A. Cooper, D. Ravich, D. Lips, J. Mayer, and H. D. Wagner, "Distribution and alignment of carbon nanotubes and nanofibrils in a polymer matrix," *Composites science and technology*, vol. 62, pp. 1105-1112, 2002.
- [86] S. Kumar, T. D. Dang, F. E. Arnold, A. R. Bhattacharyya, B. G. Min, X. Zhang, *et al.*, "Synthesis, structure, and properties of PBO/SWNT Composites&," *Macromolecules*, vol. 35, pp. 90399043, 2002.



- [87] M. Paiva, B. Zhou, K. Fernando, Y. Lin, J. Kennedy, and Y.-P. Sun, "Mechanical and morphological characterization of polymer-carbon nanocomposites from functionalized carbon nanotubes," *Carbon*, vol. 42, pp. 2849-2854, 2004.
- [88] Z. Roslaniec, G. Broza, and K. Schulte, "Nanocomposites based on multiblock polyester elastomers (PEE) and carbon nanotubes (CNT)," *Composite Interfaces*, vol. 10, pp. 95-102, 2003.
- [89] P. Pötschke, A. R. Bhattacharyya, A. Janke, and H. Goering, "Melt mixing of polycarbonate/multi-wall carbon nanotube composites," *Composite Interfaces*, vol. 10, pp. 389-404, 2003.
- [90] O. Meincke, D. Kaempfer, H. Weickmann, C. Friedrich, M. Vathauer, and H. Warth, "Mechanical properties and electrical conductivity of carbon-nanotube filled polyamide-6 and its blends with acrylonitrile/butadiene/styrene," *Polymer*, vol. 45, pp. 739-748, 2004.
- [91] T. Liu, I. Y. Phang, L. Shen, S. Y. Chow, and W.-D. Zhang, "Morphology and mechanical properties of multiwalled carbon nanotubes reinforced nylon-6 composites," *Macromolecules*, vol. 37, pp. 7214-7222, 2004.
- [92] D. Bikiaris, "Microstructure and properties of polypropylene/carbon nanotube nanocomposites," *Materials*, vol. 3, pp. 2884-2946, 2010.
- [93] M. M. Shokrieh, A. Saeedi, and M. Chitsazzadeh, "Mechanical properties of multi-walled carbon nanotube/polyester nanocomposites," *Journal of Nanostructure in Chemistry*, vol. 3, p. 20, 2013.
- [94] P. Zhang, D. Qiu, H. Chen, J. Sun, J. Wang, C. Qin, *et al.*, "Preparation of MWCNTs grafted with polyvinyl alcohol through Friedel-Crafts alkylation and their composite fibers with enhanced mechanical properties," *Journal of Materials Chemistry A*, vol. 3, pp. 1442-1449, 2015.
- [95] J. Jyoti, S. Basu, B. P. Singh, and S. Dhakate, "Superior mechanical and electrical properties of multiwall carbon nanotube reinforced acrylonitrile butadiene styrene high performance composites," *Composites Part B: Engineering*, vol. 83, pp. 58-65, 2015.
- [96] J. Gao, M. E. Itkis, A. Yu, E. Bekyarova, B. Zhao, and R. C. Haddon, "Continuous spinning of a single-walled carbon nanotube-nylon composite fiber," *Journal of the American Chemical Society*, vol. 127, pp. 3847-3854, 2005.
- [97] J. Shin, C. Kim, and K. E. Geckeler, "Single-walled carbon nanotube-polystyrene nanocomposites: dispersing nanotubes in organic media," *Polymer International*, vol. 58, pp. 579-583, 2009.
- [98] A. M. Esawi, H. G. Salem, H. M. Hussein, and A. R. Ramadan, "Effect of processing technique on the dispersion of carbon nanotubes within polypropylene carbon nanotube-composites and its effect on their mechanical properties," *Polymer composites*, vol. 31, pp. 772-780, 2010.
- [99] J. Chen, B. Liu, X. Gao, and D. Xu, "A review of the interfacial characteristics of polymer nanocomposites containing carbon nanotubes," *RSC Advances*, vol. 8, pp. 28048-28085, 2018.
- [100] T. Fornes, J. Baur, Y. Sabba, and E. Thomas, "Morphology and properties of melt-spun polycarbonate fibers containing single-and multi-wall carbon nanotubes," *Polymer*, vol. 47, pp. 1704-1714, 2006.
- [101] M. Sennett, E. Welsh, J. Wright, W. Li, J. Wen, and Z. Ren, "Dispersion and alignment of carbon nanotubes in polycarbonate," *MRS Online Proceedings Library Archive*, vol. 706, 2001.
- [102] J. Jang, J. Bae, and S.-H. Yoon, "A study on the effect of surface treatment of carbon nanotubes for liquid crystalline epoxide-carbon nanotube composites," *Journal of Materials Chemistry*, vol. 13, pp. 676-681, 2003.
- [103] W. Feng, X. Bai, Y. Lian, J. Liang, X. Wang, and K. Yoshino, "Well-aligned polyaniline/carbonnanotube composite films grown by in-situ aniline polymerization," *Carbon*, vol. 41, pp. 1551-1557, 2003.
- [104] P. Ajayan, O. Stephan, C. Colliex, and D. Trauth, "Aligned carbon nanotube arrays formed by cutting a polymer resin-nanotube composite," *Science*, vol. 265, pp. 1212-1214, 1994.
- [105] T. Kimura, H. Ago, M. Tobita, S. Ohshima, M. Kyotani, and M. Yumura, "Polymer composites of carbon nanotubes aligned by a magnetic field," *Advanced materials*, vol. 14, pp. 1380-1383, 2002.
- [106] R. Sen, B. Zhao, D. Perea, M. E. Itkis, H. Hu, J. Love, *et al.*, "Preparation of single-walled carbon nanotube reinforced polystyrene and polyurethane nanofibers and membranes by electrospinning," *Nano letters*, vol. 4, pp. 459-464, 2004.
- [107] M. D. Lynch and D. L. Patrick, "Organizing carbon nanotubes with liquid crystals," *Nano letters*, vol. 2, pp. 1197-1201, 2002.
- [108] K. S. Khare, F. Khabaz, and R. Khare, "Effect of carbon nanotube functionalization on mechanical and thermal properties of cross-linked epoxy-carbon nanotube nanocomposites: role of strengthening the interfacial interactions," *ACS applied materials & interfaces*, vol. 6, pp. 6098-6110, 2014.
- [109] C. Wang, J. Xu, J. Yang, Y. Qian, and H. Liu, "In-situ polymerization and multifunctional properties of surface-modified multiwalled carbon nanotube-reinforced polyimide nanocomposites," *High Performance Polymers*, vol. 29, pp. 797-807, 2017.



- [110] Z.-K. Chen, J.-P. Yang, Q.-Q. Ni, S.-Y. Fu, and Y.-G. Huang, "Reinforcement of epoxy resins with multi-walled carbon nanotubes for enhancing cryogenic mechanical properties," *Polymer*, vol. 50, pp. 4753-4759, 2009.
- [111] F. Gojny, M. Wichmann, U. Köpke, B. Fiedler, and K. Schulte, "Carbon nanotube-reinforced epoxy-composites: enhanced stiffness and fracture toughness at low nanotube content," *Composites science and technology*, vol. 64, pp. 2363-2371, 2004.
- [112] R. Andrews and M. Weisenberger, "Carbon nanotube polymer composites," *Current Opinion in Solid State and Materials Science*, vol. 8, pp. 31-37, 2004.
- [113] J. Cha, G. H. Jun, J. K. Park, J. C. Kim, H. J. Ryu, and S. H. Hong, "Improvement of modulus, strength and fracture toughness of CNT/Epoxy nanocomposites through the functionalization of carbon nanotubes," *Composites Part B: Engineering*, vol. 129, pp. 169-179, 2017.
- [114] Y. Chen, B. Liu, X. He, Y. Huang, and K. Hwang, "Failure analysis and the optimal toughness design of carbon nanotube-reinforced composites," *Composites Science and Technology*, vol. 70, pp. 1360-1367, 2010.
- [115] C. Ma, H.-Y. Liu, X. Du, L. Mach, F. Xu, and Y.-W. Mai, "Fracture resistance, thermal and electrical properties of epoxy composites containing aligned carbon nanotubes by low magnetic field," *Composites Science and Technology*, vol. 114, pp. 126-135, 2015.
- [116] M. Ayatollahi, S. Shadlou, and M. Shokrieh, "Fracture toughness of epoxy/multi-walled carbon nanotube nanocomposites under bending and shear loading conditions," *Materials & Design*, vol. 32, pp. 2115-2124, 2011.
- [117] F. H. Gojny, M. H. Wichmann, B. Fiedler, and K. Schulte, "Influence of different carbon nanotubes on the mechanical properties of epoxy matrix composites—a comparative study," *Composites Science and Technology*, vol. 65, pp. 2300-2313, 2005.
- [118] B. Coto, I. Antia, J. Barriga, M. Blanco, and J.-R. Sarasua, "Influence of the geometrical properties of the carbon nanotubes on the interfacial behavior of epoxy/CNT composites: a molecular modelling approach," *Computational Materials Science*, vol. 79, pp. 99-104, 2013.